

Characteristics

Feature	Rating	Hints
Alcohol- and gasoline resistance	★★★	Use of Series 600-HDA (5-10 %) to further improve resistance.
Resistance to adhesives	★★★	
Block resistance	★★★★	
Flexibility	★★★★	
Gloss	★	Mat
Resistance to hand sweat	★★★★	
Light fastness	★★★★	See technical information: light fastness
Abrasion resistance	★★★	
Pigmentation	★★★★★	
Sieve openness	★★★★	
Temperature resistance	★★★	
Drying	★★★	
Moldability	★★★★	
Weather resistance	★★★	

Legend ★★★★★ Very good product properties n/a No information available
 ★ Product properties not available

Product Range

MS Basic Colors

Article	Color	HP	HL		Article	Color	HP	HL	
388-1000	MS light yellow	•			388-3150	MS medium red		•	
388-1050	MS pure yellow		•		388-3200	MS dark red	•	•	
388-1100	MS medium yellow	•	•		388-3300	MS magenta	•	•	
388-1200	MS dark yellow	•			388-4000	MS violet	•	•	
388-1300	MS yellow orange		•		388-4500	MS dark blue		•	
388-2000	MS orange	•			388-5000	MS blue	•	•	
388-2100	MS pure orange		•		388-6000	MS green	•	•	
388-2500	MS orange red		•		388-7000	MS brown	•	•	
388-3000	MS red	•			388-8000	MS black	•	•	
388-3100	MS magenta red	•	•		388-9000	MS white	•	•	

HP High pigmented **HL** High lightfast

Note I: The MS-basic inks must be processed in combination with the corresponding binder Series 387-07 (min. 20 up to 30% by weight).
 Note II: All abbreviations used in this chart are explained in detail on the last page of this data sheet.

Other Colors

ST Colors	ST Color Chart / www.printcolor.ch/stcolorguide	
ST Metallics	ST Color Chart / www.printcolor.ch/stcolorguide	
ST Neon Colors	ST Color Chart / www.printcolor.ch/stcolorguide	
ST Process Inks	See technical information: Process Inks	
Special Colors	Pantone®, HKS, RAL and after customers sample	
Others	Series 387-00	ST white
	Series 387-04	ST transparent paste
	Series 387-05	ST varnish
	Series 387-06	Retarder paste
	Series 387-07	Binder, glossy
	Series 387-33	ST black

Auxiliaries

Thinner	Series 300-017	Addition ratio	15 – 30% by weight
Thinner for process colors	Series 300-017/ISO	Addition ratio	15 – 30% by weight
Retarder	Series 300-018	Addition ratio	max. 20% by weight
Retarder for process colors	Series 300-018/ISO	Addition ratio	max. 15% by weight
Accelerator	Series 300-019	Addition ratio	15 – 30% by weight

Note: a detailed overview of all available auxiliaries can be found in a separate data sheet.

Processing

Mesh

All commercially available polyester can be used.

Stencils

All commercially available and solvent resistant stencils can be used.

Drying

Drying of Series 387 depends on the layer thickness as well as on the substrate and the auxiliaries used.

Usual parameters (without addition of retarder):

Air	Physically fast drying at 20°C ambient temperature / 50% relative humidity. Overprintable after 5-10 minutes.
Continuous dryer	Depending on dryer capacity, the print is stackable after 30-60 seconds. The recommended drying temperature lies between 40-60°C.

Further Processing

- › Punching
- › Cutting
- › Laminating
- › Grooving
- › Thermal forming / embossing
- › Folding

Cleaning

Stencils and squeegees should timely be leaned with the products Series 300-URS or Series 300-BRS.

Special Features & Tips

Mixing system (MS) MS ink Series 388 + Binder Series 387-07 (min. 20% up to max. 30% by weight)

Productivity

Depending on color shade and substrate, a productivity of 50-70 m²/kg is to be expected with press-ready ink (20% thinning) and use of a mesh 120.34.

Others

Delivery 1 kg / 5 kg / 25 kg

Certificates / Standards www.printcolor.ch/certificates

Other Stir well before use

Information on shelf life can be found on the cover label.

Basic Color Systems

HP Basic mixing system with highly pigmented primary colors

HL High light fast color for long-term outdoor use.

Safety Information

Actual Material Safety Data Sheets according to EC-Regulation 1907/2006 are available for all products mentioned in this data sheet.

Issued on	Revised on	Edited by	Version
04.11.2014	074.02.2015	T02 / T12 / T06	2

Important Information

Our technical advice whether spoken, written, or through test trials corresponds to our current knowledge to inform about our products and their use. This is not meant as an assurance for certain properties of the products nor their suitability for each application. You are, therefore, obliged to conduct your own tests with our supplied products to confirm their suitability for the desired process or purpose. The selection and testing of the ink for specific applications is exclusively your responsibility. Should, however, any liability claims arise, such claims shall be limited to the value of the goods delivered by us and utilized by you with respect to any and all damages not caused intentionally or by gross negligence.