

Series 658

Highly flexible, solvent based 2C Screen Printing Ink

Highly glossy and very flexible, solvent based, 2C screen printing ink, Series 658. Ideal for printing on rubber-like materials. Typical applications are pro-

motional materials, technical components, bracelets and soft-touch surfaces.

Application

- › Technical components
- › Promotional material
- › Bracelets
- › Soft-touch surfaces
- › Flat glass (after preliminary tests)

Substrates

Substrate	Rating	Hints
Synthetic fabrics	★★★★★	
Polyurethane (PU)	★★★★	
TPE / rubber	★★★★	
Soft-touch surfaces	★★★	
Silicone	★	

Legend ★★★★★ Very well suited ★ Detailed pre-tests necessary

Note: A detailed overview of all substrates of product group 600 can be found here: www.printcolor.ch/bedruckstoffe

Characteristics

Feature	Rating	Hints
Alcohol- and gasoline resistance	★★★	
Resistance to adhesives	n/a	
Block resistance	n/a	
Flexibility	★★★★★	
Gloss	★★★	Silky glossy
Resistance to hand sweat	★★★★	
Light fastness	★★★★	See technical information: Light fastness
Abrasion resistance	★★★★	
Pigmentation	★★★★★	
Sieve openness	★★★★★	
Temperature resistance	★★★★	
Drying	★★★	
Moldability	n/a	
Water resistance	★★★★★	
Weather resistance	★★★★	

legend ★★★★★ Very good product properties n/a No information available
 ★ Product properties not available

Product Range

MS Basic Colors

Article no.	Color	HP		Article no.	Color	HP		
660-1000	MS light yellow	•		660-3300	MS magenta			
660-1100	MS medium yellow	•		660-4000	MS violet	•		
660-1200	MS dark yellow	•		660-5000	MS blue	•		
660-2000	MS orange	•		660-6000	MS green	•		
660-3000	MS red	•		660-7000	MS brown	•		
660-3100	MS magenta red	•		660-8000	MS black	•		
660-3200	MS dark red	•		660-9000	MS white	•		

HP High pigmented

Note I: all abbreviations used in this chart are explained in detail on the last page of this data sheet.

Other Colors

ST Colors	ST Color Chart / www.printcolor.ch/stcolorguide		
ST Metallics	ST Color Chart / www.printcolor.ch/stcolorguide		
ST Neon Colors	ST Color Chart / www.printcolor.ch/stcolorguide		
Special Colors	Pantone®, HKS, RAL and after customers sample		
Others	Series 660-00	ST white	
	Series 660-00/HD	ST white, highly opaque	
	Series 660-04	Thixotropic paste	
	Series 660-05	Varnish	
	Series 660-05/MT	Varnish, mat	
	Series 660-06	Retarder paste	
	Series 660-07	Binder	
	Series 660-33	ST black	

Auxiliaries

Thinner	Series 600-017	Addition ratio	10-20% by weight
Retarder	Series 600-018	Addition ratio	5-15% by weight

Hardener

	Series 600-HDA	Series 600-HDI	
Addition ratio	10:1	10:1	
Reactivity	Medium reactivity from 20°C	Higher reactivity from 15°C	
Resistance to chemicals	Good	Good	
Outdoor resistance	Good	Not recommended	

Note: a detailed overview of all available auxiliaries can be found in a separate data sheet.

Processing

Mesh

All commercially available polyester mesh can be used.

Stencils

All commercially available stencils can be used.

Curing

Bonding of the ink system depends on temperature, used hardener and layer thickness. To reach maximum resistance, a minimum temperature (see point „hardener“) must be guaranteed over a duration of 5 to 10 days. By increasing the temperature the ink film cures faster and an earlier and even better chemical resistance can be achieved.

Curing times

Series 600-HDA	7 days (at minimum temperature)
Series 600-HDI	5 days (at minimum temperature)
Forced drying	20 minutes at 140°C

It is important to ensure, that temperatures do not fall below within the first 48 hours. An increased moisture supply during drying time can permanently damage the ink film.

Pot life

MS colors and its blends have a pot life of 4-8 hours, depending from the hardeners used and depending on environmental conditions. Significantly shortened pot life has to be encountered with metallic colors.

Overprintability

The ink film can be overprinted preferably before complete curing of the ink.

Further Processing

After preliminary tests

Cleaning

Intermediate cleaning of stencils and squeegees should be done in a timely manner with Series 600-BRS. Final cleaning can be done with Series 600-URS.

Special Features & Tips

Prolonged curing Because of the highly flexible binder, a prolonged curing time has to be expected. It can thus be reduced by use of HDI-hardener for indoor use.

Productivity

Depending on the color shade, a productivity of 45-65 m²/kg is to be expected with press-ready ink and use of a mesh 120.34.

Others

Delivery	1 kg / 5 kg / 25 kg
Certificates / Standards	www.printcolor.ch/certificate
Others	Stir well before use. Information on shelf life can be found on the cover label.

Basic Color Systems

HP Basic Color Mixing System with high pigmented basic colors.

Safety Information

Actual Material Safety Data Sheets according to EC-Regulation 1907/2006 are available for all products, mentioned in this data sheet.

Issued on	Revision on	Edited by	Version
31/08/2015	-	T21 / T06	1

Important Information

Our technical advice whether spoken, written, or through test trials corresponds to our current knowledge to inform about our products and their use. This is not meant as an assurance for certain properties of the products nor for their suitability for each application. You are, therefore, obliged to conduct your own tests with our supplied products to confirm their suitability for the desired process or purpose. The selection and testing of the ink for specific applications is exclusively your responsibility. Should, however, any liability claims arise, such claims shall be limited to the value of the goods delivered by us and utilized by you with respect to any and all damages not caused intentionally or by gross negligence.