

INK SERIES	SERIES 711	SERIES 712	SERIES 747	SERIES 750	SERIES 751	SERIES 752	SERIES 784	SERIES 786	SERIES 792
SYSTEM	S 1C	S 1C	UV	S 2C	S 2C	S	S 2C	S 2C	S 2C
ABS / SAN	★		★	★ H	★ H	★ (H)	★ H	★ H	
Acrylics (PMMA)	★		★	★ H	★ H	★ (H)	★ H	★ H	
Duroplastics			★	★ H	★ H	★ (H)	★ H	★ H	
Glass & Ceramic			★	★ H	★ H				
Laquered surfaces	★		★	★ H	★ H	★ (H)	★ H	★ H	★ H
Metal			☆	★ H	★ H	☆ (H)	★ H	★ H	
PET-A	★		★			★ (H)	★ H	★ H	
PET-G						★ (H)			
Polyamid (PA)			★	★ H	★ H	★ (H)	★ H	★ H	
Polycarbonate (PC)	★		★	★ H	★ H	★ (H)	★ H	★ H	
Polyester	☆		☆	★ H	★ H	★ (H)	★ H	★ H	
Polyethylene (PE)			★🔥	★🔥H	★🔥H	★🔥(H)	★🔥H	★🔥H	
Polyoxymethylene (POM)				★ H	★ H				
Polypropylene (PP)		★	★🔥	★🔥H	★🔥H	★🔥(H)	★🔥H	★🔥H	
Polystyrole (PS)	★		★			★ (H)	★ H	★ H	
PVC, rigid	★		★	★ H	★ H	★ (H)	★ H	★ H	
PVC, soft	★		★			★ (H)			
TPE / Rubber									★ H
Tritan™ (Copolyester)							★ H	★ H	

INDEX **S** = Solvent **WB** = Water based **UV** = UV curing ★ = suitable ☆ = Inspection necessary **H** = Hardener **(H)** = Also 1C processable 🔥 = only after pre-treatment

More detailed information is contained in the technical data sheet (www.printcolor.swiss/tds).